

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (original): A rubber composition for a tread characterized by compounding (a) 5-40 parts by mass of a softening agent including an oil in which an extraction quantity with dimethylsulfoxide (DMSO) by IP346 process is controlled to less than 3% by mass and (b) 5-40 parts by mass of a liquid polymer having a viscosity average molecular weight of 45,000-100,000 based on 100 parts by mass of a rubber component.
2. (original): A rubber composition for a tread according to claim 1, wherein the viscosity average molecular weight of the liquid polymer is 55,000-85,000.
3. (currently amended): A rubber composition for a tread according to claim 1 ~~or 2~~, wherein the liquid polymer is a liquid styrene-butadiene copolymer.
4. (original): A rubber composition for a tread according to claim 1, wherein the oil is at least one process oil selected from the group consisting of T-DAE and MES.
5. (original): A rubber composition for a tread according to claim 1, wherein the softening agent (a) further contains a hydrogenated naphthenic oil.
6. (original): A rubber composition for a tread according to claim 5, wherein the hydrogenated naphthenic oil is obtained by hydrogenating a naphthenic oil in which a content of naphthenic hydrocarbon (%CN) measured according to ASTM D2140 is not less than 30.

7. (currently amended): A rubber composition for a tread according to claim ~~5 or 6~~, wherein the softening agent (a) further contains asphalt having a dynamic viscosity at 120°C of not more than 300 mm<sup>2</sup>/sec and an asphaltene content of not more than 5% by mass at a mass ratio of hydrogenated naphthenic oil/asphalt of 95/5-5/95.

8. (currently amended): A tire characterized by using a rubber composition as claimed in ~~any one of claims 1 to 7~~claim 1 in a tread.

9. (new): A rubber composition for a tread according to claim 2, wherein the liquid polymer is a liquid styrene-butadiene copolymer.

10. (new): A rubber composition for a tread according to claim 6, wherein the softening agent (a) further contains asphalt having a dynamic viscosity at 120°C of not more than 300 mm<sup>2</sup>/sec and an asphaltene content of not more than 5% by mass at a mass ratio of hydrogenated naphthenic oil/asphalt of 95/5-5/95.

11. (new): A tire characterized by using a rubber composition as claimed in claim 2 in a tread.

12. (new): A tire characterized by using a rubber composition as claimed in claim 3 in a tread.

13. (new): A tire characterized by using a rubber composition as claimed in claim 4 in a tread.

14. (new): A tire characterized by using a rubber composition as claimed in claim 5 in a tread.

15. (new): A tire characterized by using a rubber composition as claimed in claim 6 in a tread.

16. (new): A tire characterized by using a rubber composition as claimed in claim 7 in a tread.

17. (new): A tire characterized by using a rubber composition as claimed in claim 9 in a tread.

18. (new): A tire characterized by using a rubber composition as claimed in claim 10 in a tread.